TUNGCHIP DISPENSER

An improved feeder design allows for accurate delivery of Tungchip Tungsten Carbide Grit into the molten weld pool, generated by a MIG (GMAW) welding system.

INCLUDED IN THE SYSTEM ARE THE FOLLOWING:

- Vibratory feeder assembly, fully enclosed including mounting bolts.
- Control box with two way power switch on-off, power light and electrical noise suppression, soft start and two-way bypass switch.
- Foot pedal control or optional sensor switch activation.
- NB All external devices operate at 24 volts DC for safe user operation.
- Cabling protected with PVC spiral sheath.
- Powder coated Tungchip hopper.
- 1.5 metres of clear wire-wound drop hose.
- ±150mm SS metering tube with clamp for MIG gun mounting (MIG gun not included).
- Ceramic replaceable TIG nozzle.
- 220-240V AC line cable.
- All screws and nuts for assembly to a base plate.





CONTROL FUNCTION AND OVERALL DESCRIPTION OF THE SYSTEM:

POWER

Is supplied to this system via a 230V AC 50 cycle line cable with threeprong plug, for Australia/NZ, or two-prong German style.

POWER SWITCH

When the toggle switch is switched on, the feeder will not commence until the foot pedal, or sensor switch is engaged.

BYPASS SWITCH

This enables the feeder to operate without the foot pedal being engaged.

CARBIDE FEED RATE

The carbide feed rate is controlled by a single turn potentiometer, utilizing phase angle control principles.

MOUNTING

3 bolts are provided to mount unit on your mount plate. These are stand alone and not part of the vibrator.

CARBIDE FEED

The advantage of this trough fed system is that it can accurately meter any size of Tungchip Tungsten Carbide Grit or particle without the need to add any new system component or adjust any component of the system other than the potentiometer. The feed rate potentiometer allows for a wide range of feed rates with a simple turn of the dial, while the unit is in full operation. There is no need to stop in order to make and test mechanical adjustments. The foot pedal allows you ease of control, the unit can be preset and Tungchip Tungsten Carbide Grit feed commences by pressing the foot pedal

ADDITIONAL INFORMATION ON WELDING WITH MIG CARBIDE

PREPARATION

Always try to grind the weld area to clean and remove any oxide build up (rust). Many shops do not clean to save time and money, the surface does not have to be perfect.

WIRE

The most versatile wire size is ± 1.2 mm LH/S6 wire. This wire can be used with the higher voltage and lower amps to make thinner weld beads with deep penetration. The best wires are triple or double deoxidized, low hydrogen. They make a very clean puddle for the carbide to drop through and have a high tolerance for dirty base metal surfaces. Using Ni Cr wires provides good resistance against corrosion and increases working temperature. Alloyed wires like manganese / chrome alloys allow the matrix to harden and have been found to be successful in certain light impact applications.

CARBIDE DEPOSITIONS

Many MIG carbide users are now favouring 12 x 20 mesh size or something close to this range. Some customers have found that for very fine particle abrasion 20 x 30 mesh is a better size. A good choice for general service is the 12 x 30 mesh size. For pure rock service 20 x 30 mesh, has been found to be successful. When working in mixed materials that are damp and tend to clump together, a larger particle will tend to attract the material, assisting with material on material wear. This is general information obtained from customer's experiments and comments. We recommend you undertake your own trials.

SCREENING USED CARBIDE

After several cycles, used carbide tends to pick up over-sized particles, splatter, dust, dirt, etc. This contamination will begin to affect the feed ability and the quality of the weld. Screen the recycled carbide through 200 - 400mm diameter sieve screens of the same mesh as your carbide. For example, if you are using 12 x 20 carbide, buy two screens and one bottom pan. The top set would be 12 mesh. The middle set will be 20 mesh. Discard or re-crush everything on top of the 12 mesh and dispose of everything in the bottom pan (environmentally correctly). Screens available on request.

GASES AND VOLTAGES

Argon/O2(2%) is the most popular mix. Pure Argon is also used; however it is not as popular. 75/25 (75% Argon/25% CO2) is another choice. Pure CO2 is the cheapest gas and can be used with high voltage. The higher the voltage the more penetration and the flatter the bead will be. All gases can be used with high or low voltage.

| • | Low Heat | 24-26 volts |
|---|-------------|-------------|
| • | Medium Heat | 27-29 volts |

• Hot

30-33 volts

MINIMIZING DISTORTION

To minimize distortion (especially on thinner parts), use lower volts and amps with pure Argon. Use preheats on all parts to eliminate or minimize distortion. Most thick and wide cutting edges can be made perfectly flat with only preheat. Thinner parts should be pre-bowed and warped (along the preheat). This information is used as a guide only. It is recommended that you undertake trials yourself to evaluate the particular alloy and product you are working with.

TYPICAL WELD SETTING

Weld settings for medium weld speeds would be the following:

- Wire Size: 1.15mm 1.6mm 2.36mm
- Volts (V) : 29-30 29-31 30-32
- Amps (A): 230-245 290-300 325-360
- Gas : Argon or Argon/O2
- Low flat bead shape with medium penetration

WELDING TECHNIQUES

Single layer welds are recommended. Multiple layers tend to dissolve the carbide in the lower layers and produce a very hard deposit that will chip and break off with only light impact. Use oscillated beads about 15mm-25mm wide (37mm max). Oscillation frequency should be 70-85 cps (cycles per second). Aim carbide into the trailing side of the arc puddle. The aim point is critical for good carbide distribution. If these basic parameters are followed, consistent and reliable work can be readily produced by any weld shop. The process. Product and application variances must be taken into account before applying Tungchip Tungsten Carbide Grit.

Designed and Assembled in Australia

Our products and any recommended practices, should be tested by the user under actual service conditions to determine their suitability for any particular purpose. The results obtained using this product / information are affected by variables such as welding procedure, base material composition, operating temperature, weldmet design, method of fabrication and service requirements which are beyond our control. It is the sole responsibility of the user to determine the serviceability of a structure using this product and the information contained in this data sheet. The technical information given in this data sheet reflects the present state of knowledge and does not form part of any sales contract as guaranteed properties of the delivered materials.

